

Magnetic field relaxation in ferromagnetic Ising systems

R. Mélin

CRTBT-CNRS, 38042 Grenoble BP 166X cédex France

Abstract

We analyze the thermal magnetization reversal processes in magnetic grains. Two experiments are carried out: switching time and switching field experiments. In both cases, we find that the simulated behavior is coherent with existing experimental data (the stretched exponent of the switching time experiment increases with the temperature and is superior to unity; there exists a master curve for the switching field experiment). Moreover, we simulated magnetic grains in a region of parameters where no experimental data are available. We find that the relaxation time distribution $P(\ln \tau)$ is gaussian, and we find the existence of a strong field regime.

Contents

1	Switching time experiment	2
1.1	Square lattice with free boundary conditions	2
1.2	Distribution $P(\ln \tau)$	3
1.3	Mean value and variance of the relaxation time distribution	3
1.4	Stretched exponent β	4
2	Switching field experiment	5
3	Conclusion	5

Magnetic grains are considered as good candidates to bring to the fore macroscopic quantum tunnelling [1]. Before considering the problem of quantum tunneling at low temperatures, it would first be interesting to understand thermally activated processes at higher temperature. The aim of the present paper is to address this question in a simplified model. Experimentally, small ferromagnetic grains were studied for many years in powders, so that data were available only for a collection of interacting magnetic grains, with different sizes and compositions. Using magnetic force microscopy [2] and Lorentz microscopy [3], it was possible to resolve the magnetic properties of individual single-domain particles. The present article is based on the experimental works [4], where it was possible to study the magnetization reversal of a single monodomain magnetic particle of size $0.1\mu m \times 0.05\mu m$. Due to dipolar interactions, anisotropy aligns the spins along the largest direction of the grain. The spins are essentially XY spins since the grain is essentially bidimensional. We do not carry out direct simulations of XY spins at finite temperature, but, instead, we consider a simplified Ising spin model on a disk to simulate a magnetic grain. This means that a direct comparison with the experimental exchange couplings and magnetic field is not possible. However, we believe that our simulations are qualitatively valid, even though they do not directly represent magnetic grains. The reason why we choose the disk geometry is that the frontier is expected to play a great role in the magnetization reversal processes. In [5], the boundary conditions are periodic, so that boundary effects are not properly taken into account. In order to compare with existing experiments [4], we use the same experimental techniques than in [4]. Two types of experiments are possible 1) switching time experiments 2) switching field experiments.

In the first class of simulations, the system starts in a low temperature configuration where nearly all the spins are parallel. A constant magnetic field opposite to the initial magnetization is applied from time $t = 0$. The initial configuration, antiparallel to the field, is then metastable, and the magnetization reverses to the opposite magnetization. The time τ corresponding to the cancellation of the magnetization is recorded. Since the reversal of magnetization process is stochastic, τ is a random variable. In our simulations, we took

into account 30000 different runs. This number is necessarily huge in order to have a good statistics. In existing experiments, data with such an important number of reversal processes are not available at the moment, so that some of the results that are reported here are not directly comparable to experimental data because of the lack of experimental data in these temperature and field ranges. We first show that the distribution $P(\ln \tau)$ of the logarithm of the relaxation times is gaussian. This result is in agreement with other theories, especially for spin glasses [6], where a gaussian distribution of the logarithm relaxation times has been assumed, in the context of a phenomenological renormalization. We also analyze the mean value $\langle \ln \tau \rangle$, and the variance $\langle (\ln \tau - \langle \ln \tau \rangle)^2 \rangle$ as a function of temperature. We find that, if the field is not too strong, both the mean value and the variance diverge as T approaches zero. If the field is too strong, the divergence is replaced by a saturation of these two quantities, so that long relaxation times at low temperature are inhibited by a too strong magnetic field. This qualitative behavior between a strong magnetic field regime and a weaker magnetic field regime is to be compared with the results of [5], where a strong magnetic field regime is exhibited. In the switching time experiments, we can study the variations of $\langle \ln \tau \rangle$ as a function of the variance $\langle (\ln \tau - \langle \ln \tau \rangle)^2 \rangle$. Within the context of phenomenological spin glass theories [6], this curve is expected to be linear. However, we do not find linear variations. Depending on the strength of the magnetic field, the curvature is negative (strong magnetic fields) or positive (weak magnetic fields).

The second possible class of experiments is the so-called switching field experiments. The idea is to start from a low temperature configuration, and to switch a field opposite to the global magnetization. The field increases linearly with a rate $\nu = -dH/dt$. In the presence of the external field, the magnetization reverses and one measures the magnetic field H_{sw} for which the magnetization cancels. The switching field H_{sw} is averaged over a large number of runs, and computed for various temperatures. In order to analyze the data, we use the phenomenological model of reference [7]. We find that, as in real experiments, there exists a master curve for $\langle H_{sw} \rangle(T, \nu)$.

1 Switching time experiment

1.1 Square lattice with free boundary conditions

In order to emphasize the importance of the boundary conditions, we first consider the case of an Ising model on a square. In this case, the domains of reversed spins can nucleate from the corner. The barrier to nucleate a domain of spins parallel to the magnetic field is $E_1(R) = \pi R(J - hR/2)$, where we have assumed that the domain of reversed spins is circular (this is an approximation, since the droplets are not necessarily circular). The maximum over

R of $E_1(R)$ is nothing but the barrier that need to be paid to reverse the magnetization. This barrier is $E_1(R_1^*) = \pi J^2/2h$. In order to compare with the absence of edges (Ising model on a disk), we calculate the barrier to nucleate a domain of spins paralell to the field on the disk. We assume that the radius of the disk is large compared to the radius of curvature of the droplet. The barrier is given by $E_2(R) = 2\pi R(2J - hR)$. The first term $4\pi RJ$ is the energy term associated to the antiparallel links at the boundary and $-2\pi hR^2$ is the magnetic energy. $E_2(R)$ is maximum for $R_2^* = J/h$, which corresponds to the critical size of the domain. If $R < R_2^*$, the domain has a trend to regress whereas it naturally grows if $R > R_2^*$. The barrier height is $E_2(R_2^*) = 2\pi J^2/h$. We see that the barrier in the presence of edges is one half of the barrier in the absence of edges, from what we conclude that the spin system on a square with open boundary conditions is very sensitive to the presence of edges and will first flip from the edges, at least if the magnetic field is not too strong. To check this assertion, we took a snapshot of the system during a given run. The result is pictured on figure 1. It is clear that the edges play an important role in the magnetization reversal, since the droplets are pinned at the edges, where the energy barrier is smaller than in the bulk. The pinning of the droplets is here purely geometric. One could also imagine that the droplets are pinned due to the presence of impurities.

In what follows, we aim to elimitate the corner nucleation of domains. This is why we consider an Ising model on a disk, with free boundary conditions.

1.2 Distribution $P(\ln \tau)$

We call τ the time corresponding to the cancelation of the magnetization. We plotted on figure 2 the distribution $P(\ln \tau)$ as a function of $\ln \tau$. We see that these distribution in very good agreement with gaussian distributions. This means that the distribution of relaxation times in an external magnetic field is gaussian, provided one uses the logarithm of the relaxation times. This result is in agreement with the assumption of [6]. In the context of spin glasses, it is assumed that $P(\ln \tau)$ is Gaussian. However, as we will see later, not all the assumptions of this phenomenological theory are valid in our model.

1.3 Mean value and variance of the relaxation time distribution

Since $P(\ln \tau)$ is a well defined gaussian distribution, we can study the variations of $\langle \ln \tau \rangle$ and of the variance $\langle (\ln \tau - \langle \ln \tau \rangle)^2 \rangle$ as a function of temperature. We first begin with the mean value $\langle \ln \tau \rangle$. The results for three different magnetic fields are plotted on figure 3. We observe that if the intensity of the magnetic field decreases, the relaxation times increase. Moreover, if there exists a critical value h^* f the magnetic field such that if $|h| < h^*$, the relaxation times diverges in the zero temperature limit, whereas if $|h| > h^*$, the relaxation times saturate in the

zero temperature limit. We identify this behavior with the existence of the strong magnetic field regime of reference [5].

The variations of the variance $\langle(\ln \tau - \langle \ln \tau \rangle)^2\rangle$ as a function of temperature are plotted on figure 4. These variations are qualitatively similar to the variations of the mean value: if the intensity of the magnetic field is too strong, we observe a saturation of the variance, whereas it diverges for weaker magnetic fields.

We are now in position to study the variations of the mean value $\langle \ln \tau \rangle$ as a function of the variance $\langle(\ln \tau - \langle \ln \tau \rangle)^2\rangle$. These variations are pictured on figure 5. We observe that in the strong magnetic field region, the variance and the mean value are quite small, and both tend to a constant if the temperature decreases to zero. By contrast, we observe that if $h = -1.5$, the curvature is negative, whereas it is positive if $h = -1$. It would be interesting to know whether experimental on magnetic grains could confirm these simulations. However, these data are not available at the moment, due essentially to the fact that it is necessary to repeat the experience a large number of times to obtain a good statistics, and also to the fact that the experiments are not carried out for a given magnetic field, in order to avoid very long relaxation times. If we compare our results to the prediction of spin glass theory [6], we do not find that $\langle \ln \tau \rangle$ is linear as a function of $\langle(\ln \tau - \langle \ln \tau \rangle)^2\rangle$, and, according to the strength of the magnetic field, we find a positive or a negative curvature. We conclude that our model for thermal magnetic grains shares some common features with spin glasses since $P(\ln \tau)$ is found to be gaussian in both cases. However, whereas spin glasses phenomenological models predict a linear variation of $\langle \ln \tau \rangle$ as a function of the variance $\langle(\ln \tau - \langle \ln \tau \rangle)^2\rangle$, we do not find here such a linear behavior.

1.4 Stretched exponent β

Another possible analysis of the data of the switching time experiment is to build the histogram $P(\tau)$, and to fit the integrated histogram by a stretched exponential

$$\int_0^\tau P(\tau') d\tau' \simeq 1 - \exp\left(-\left(\frac{\tau}{\tau_0}\right)^\beta\right). \quad (1)$$

This analysis is carried out on experimental data in [4], where the stretched exponent β is studied as a function of temperature. The main results are that β increases with temperature, and may be superior to unity. As we shall see, our simulations agree with these two experimental facts. At this point, it should be underlined that the stretched exponent β has nothing to do with the stretched exponent of [8] in the context of spin glasses. In [8], the autocorrelation functions of spin glasses are fitted by a stretched exponential, and a stretched exponent is deduced from the numerical data. In this case, the stretched exponent is necessary inferior to unity, whereas in what we study, the stretched exponent may be larger than unity.

We show on figure 6 the variation of the stretched exponent β as a function of T , for two magnetic fields. It is clear that β increases with T , and may be superior to unity. We also observe that the stretched exponent increases if the strength of the magnetic field increases, which is coherent with the fact both the mean value $\langle \ln \tau \rangle$ and the variance $\langle (\ln \tau - \langle \ln \tau \rangle)^2 \rangle$ decrease if the strength of the magnetic field increases.

2 Switching field experiment

In the switching field experiment, a linearly increasing magnetic field is applied opposite to the direction of the initial magnetization, with a rate $\nu = -dH/dt$. The magnetic field H_{sw} corresponding to the cancellation of the magnetization is measured. In order to analyze the data, we follow reference [4], and use the phenomenological model of [7]. In this model, the average switching field $\langle H_{sw} \rangle$ is given by

$$\langle H_{sw} \rangle = H_{sw}^0 (1 - f_\alpha(T, \nu)), \quad (2)$$

with

$$f_\alpha(T, \nu) = \left(\frac{k_B T}{E_0} \ln \left(\frac{cT}{\nu \epsilon^{\alpha-1}} \right) \right)^{1/\alpha} \quad (3)$$

H_{sw}^0 , E_0 and c are some constants, $\alpha = 2$ for an ideal single domain model and

$$\epsilon = (1 - H_{sw}/H_{sw}^0)^{1/\alpha}. \quad (4)$$

The experimental data consist of $\langle H_{sw} \rangle(T, \nu)$ as a function of the temperature T and the switching rate ν . The relation (2) predicts the existence of a master curve for $\langle H_{sw} \rangle(T, \nu)$. We carried out numerical simulations for the square lattice on the disk, with open boundary conditions. We come to the conclusion that there exists a master curve for $\langle H_{sw} \rangle(T, \nu)$. The master curve is plotted on figure 7. We see that there exists differences between the master curve and the behavior $\langle H_{sw} \rangle/H_{sw}^0 = 1 - f_\alpha(T, \nu)$. These deviations also exist in the experiments [4].

3 Conclusion

We have carried out numerical simulations of a simplified model of magnetic grain in the thermal regime. We have carried two types of numerical simulations: switching time and switching field experiments. As far as switching time experiments are concerned, we found a gaussian behavior for the histogram $P(\ln \tau)$ of the logarithm of the relaxation times. This behavior is compatible with existing theories of slow relaxation phenomena. We find the

existence of a strong field regime, where both $\langle \ln \tau \rangle$ and the variance $\langle (\ln \tau - \langle \ln \tau \rangle)^2 \rangle$ tend to a constant as the temperature approaches zero. This regime was already predicted in [5], and called the strong field regime. If the magnetic field is smaller, the mean value and the variance diverge as the temperature approaches zero. It would be interesting to study the magnetic field h^* , which separates the strong magnetic field region, as a function of the system size. It would also be interesting to carry out similar simulation for non Euclidian boundaries, in order to have a more precise idea of the importance of boundary effects. To do so, it is possible to study the case of a hyperbolic lattice, or a Cayley tree, with a finite fraction of the sites at the boundary even in the thermodynamic limit. Unfortunately, experimental data on magnetic grains are not available since these experiments require a large amount of data. We also calculated the stretched exponent β as a function of T . Like in the case of experiments, we find that β may be superior to unity, and that β increases with T .

We also considered the switching field experiment. There exists a master curve for the average of the switching field as a function of the switching rate and the temperature, which is consistent with the experimental data.

The author acknowledges discussion with J.C. Anglès d'Auriac, B. Barbara, B. Douçot, K. Hasselbach, J. Souletie and W. Wernsdorffer.

References

- [1] P.C.E. Stamp, E.M. Chudnovsky and B. Barbara, Int. J. of
- [2] Y. Martin and H.K. Wickramasinghe, Appl. Phys. Lett. 50, 1455 (1987); T. Chang, J.G. Zhu and J.H. Judy, J. Appl. Phys. 73, 6716 (1994); M. Lederman, G.A. Gibson and S. Schultz, J. Appl. Phys. 73, 6961 (1993); M. Lederman, D.R. Redkin, R. O'Barr and S. Schultz, J. Appl. Phys. 75, 6217 (1994); M. Lederman, S. Schultz and M. Ozaki, IEEE Trans. Magn. 27, 5184 (1991).
- [3] C. Salling, S. Schultz, I. McFayen and M. Ozaki, IEEE Trans. Magn. 27, 5184 (1991).
- [4] W. Wernsdorffer, A. Benoit, G. Cernicchiaro, D. Maillly, B. Barbara and L. Thomas, J. Magn. Magn. Mat. 151, 38 (1995); W. Wernsdorfer, K. Hasselbach, A. Sulpice, A. Benoit, J.E. Wegrowe, L. Thomas and D. Mailly, Phys. Rev. B 53, 3341 (1996).
- [5] H. L. Richards, S. W. Sides, M. A. Novotny and P. A. Rikvold, submitted to Jour. of Magnetism and Magnetic Materials (1995).
- [6] B. Castaing and J. Souletie, J. Phys. I, 403 (1991); J. Souletie, Physica A, 201, 30 (1993).
- [7] L. Gunther and B. Barbara, Phys. Rev. B 49 (1994)
- [8] A.T. Ogielski, Phys. Rev. B 32, 7384 (1985). J. Phys (France) 45, 1809 (1984).

Figure captions

Figure 1:

Snapshot of the spin configuration in a given numerical experiment, in the case of a 90x90 square lattice. The magnetization is equal to $3/4$. The inverse temperature is $\beta = 1.6J$, and the applied magnetic field is $h = -J$. A symbol denotes a down spin (parallel to the field) and the spin is up in the absence of symbol. The droplets are pinned at the corners.

Figure 2:

Distribution of $P(\ln \tau)$ as a function of $\ln \tau$ for different temperatures. The lattice is a disk with 2821 sites. The magnetic field is set to $h = -1.5$ from time $t = 0$. The different distribution and the fit to the Gaussian are plotted for $T = 0.22J, 0.20J, 0.18J, 0.16J$. 30000 runs were carried out in each case.

Figure 3:

Mean value $\langle \ln \tau \rangle$ as a function of temperature, for three values of the magnetic field $h = -2J, h = -1.5J$ and $h = -J$. The lattice is circular, with 2821 sites. 30000 runs were carried out in each case.

Figure 4:

Variance $\langle (\ln \tau - \langle \ln \tau \rangle)^2 \rangle$ as a function of temperature, for three values of the magnetic field $h = -2J, h = -1.5J$ and $h = -J$. The lattice is circular, with 2821 sites. 30000 runs were carried out in each case.

Figure 5:

Variance $\langle (\ln \tau - \langle \ln \tau \rangle)^2 \rangle$ as a function of the mean value $\langle \ln \tau \rangle$, for three values of the magnetic field $h = -2J, h = -1.5J$ and $h = -J$. The lattice is circular, with 2821 sites. 30000 runs were carried out in each case.

Figure 6:

Variations of the stretched exponent β with the temperature, and for $h = -1$ and $h = -1.5$. The lattice is circular, with 2821 sites. 30000 runs were carried out in each case.

Figure 7:

Master curve of the switching field experiment for the square lattice on the disk. We plotted $\langle H_{sw} \rangle / H_{sw}^0$ as a function of $f_\alpha(T, \nu)$. The Boltzmann constant is equal to unity, $\alpha = 1.8$, $H_{sw}^0 = 2.4$, $E_0 = 5$ and $c = 1/25$. On this curve, 7 series of measures at 7 different temperatures are superposed. The dashed line is the linear behaviour and corresponds to $\langle H_{sw} \rangle / H_{sw}^0 = 1 - f_\alpha(T, \nu)$.













